

STOCK LIST H -10

C	USA	Chemical Analysis Typical Values % (Min - Max)											Delivery Condition	
(DIN)	(AISI)	C	S	P	Si	Mn	Ni	Cr	Mo	V	W	other	Heat Treatment	Hardness
1.2365	H-10	0.28-0.35	≤0.02	≤0.03	0.10-0.40	0.15-0.45	***	2.70-3.20	2.50-300	0.40-0.70	***	****	Annealed	≤HB230

HOT WORK STEEL (DIN-1.2365) H-10 ROUND EAF +LF + VD-VOD +SPERODISED ANNEALED- - HOT ROLLED ANNEALED PEELED

16.00, 16.30, 16.50, 17.50, 18.50, 20.50, 22.50, 26.00, 28.00, 30.00, 32.00, 36.00, 40.00, 45.00, 47.00, 51.00, 56.00, 60.00, 65.00, 70.00, 76.00,

***HOT WORK STEEL (DIN-1.2365) H-10 ROUND EAF+ LF+ VD-VOD + SPERODISED ANNEALED-FORGED & TURNED**

81.00, 85.00, 90.00, 95.00,, 102.00, 106.00, 111.00, 117.00, 122.00, 132.00, 142.00, 152.00, 162.00, 172.00, 182.00, 192.00, 202.00, 206.00, 212.00, 217.00, 218.00, 222.00, 227.00, 232.00, 235.00, 242.00, 243.00, 252.00, 262.00, 272.00, 282.00, 302.00, 306.00, 312.00, 315.00, 316.00, 322.00, 332.00, 362, 382, 412, 455, 510, 560 ,610 .