

**STOCK LIST H -11 & H-11 M**

C	USA	Chemical Analysis Typical Values % (Min - Max)											Delivery Condition	
(DIN)	(AISI)	C	S	P	Si	Mn	Ni	Cr	Mo	V	W	other	Heat Treatment	Hardness
1.2343	H-11	0.33-0.41	≤0.030	≤0.030	0.80-1.20	0.20-0.50	***	4.80-5.50	4.70-5.20	1.10-1.50	***	****	Annealed	≤HB235

**HOT WORK STEEL (DIN-1.2343) H-11ROUND EAF +LF + VD-VOD +SPERODISED ANNEALED- - HOT ROLLED ANNEALED PEELED**

16.00, 16.30, 16.50, 17.50, 18.50, 20.50, 22.50, 26.00, 28.00, 30.00, 32.00, 36.00, 40.00, 45.00, 47.00, 51.00, 56.00, 60.00, 65.00, 70.00, 76.00,

**\*HOT WORK STEEL (DIN-1.2343) H-11 ROUND EAF+ LF+ VD-VOD + SPERODISED ANNEALED-FORGED & TURNED**

81.00, 85.00, 90.00, 95.00,, 102.00, 106.00, 111.00, 117.00, 122.00, 132.00, 142.00, 152.00, 162.00, 172.00, 182.00, 192.00, 202.00, 206.00, 212.00, 217.00, 218.00, 222.00, 227.00, 232.00, 235.00, 242.00, 243.00, 252.00, 262.00, 272.00, 282.00, 302.00, 306.00, 312.00, 315.00, 316.00, 322.00, 332.00, 362, 382, 412, 455, 510, 560 ,610 .

**\*HOT WORK STEEL (DIN 1.2343) H-11M(ROUND) - (MF. ROUTE: EAF+LF+VD-VOD + SPERODISED ANNEALED- FORGED & TURNED**

**S I Z E : DIA 100 TO 600 mm**